QC ABSTRACT

NAME OF WORK: "Improvements and Asphalting to Roads at Synika Vihara Badavane Main Road in Chowdeshwari Ward No -02 of Yelahanka Sub Division"

SL NO	Item Of Work	Name of Test	Frequency of Test/Quantity	Executed Quantity	Number of Tests Required	Number of Tests Conducted
		Materials				
1	Cement	Fineness by dry sieving	One Test		1	1
		Finess by Air permeablity method	One Test		1	1
		Density	One Test		1	1
		Standard Consistency	One Test		1	1
		Initial Setting time	One Test		1	1
		Final Setting time	One Test		1	1
		Soundness (Le Chatelier's Method)	One Test		1	1
		Compressive Strength	One Test		1	1
2	Coarse aggregate(40 mm down size)	SIEVE ANALYSIS	One Test		1	1
		Flakiness Index	One Test		1	1
		Elongation Index	One Test		1	1
		Specific Gravity	One Test		1	1
		Bulk Density(Loose)	One Test		1	1
		Bulk Density(Compacted)	One Test		1	1
		Water Absorption	One Test		1	1
3	Coarse aggregate(20 mm down size)	SIEVE ANALYSIS	One Test		1	1
		Flakiness Index	One Test		1	1
		Elongation Index	One Test		1	1
		Specific Gravity	One Test		1	1
		Bulk Density(Loose)	One Test		1	1
		Bulk Density(Compacted)	One Test		1	1
		Water Absorption	One Test		1	1
		Aggregate crushing Value	One Test		1	1
		Aggregate Impact Value	One Test		1	1
4	Fine aggregate	SIEVE ANALYSIS	One Test		1	1
		Water Absorption	One Test		1	1
		Specific Gravity	One Test		1	1
		Material finer than 75 micron	One Test		1	1
5	Steel	Bend test	One Test		1	1
		Tensile Test	One Test		1	1
		Yield Test	One Test		1	1
		ReBend test	One Test		1	1
6	Precast (100mm)	Core Compressive Strength	One Test		1	1
		Corrected Cylinder Compressive Strength	One Test		1	1
		Equivalent Cube Compressive Strength	One Test		1	1
7	Precast (250mm)	Core Compressive Strength	One Test		1	1
		Corrected Cylinder Compressive Strength	One Test		1	1
		Equivalent Cube Compressive Strength	One Test		1	1
8	RCC(M20)	Compressive Strength(7days and 28days)	5 set /51-100 cum	57.6	10	10

AE-02

Format No: CP/TF/01

TEST REPORT OF FINE AGGREGATE

Lab ID	:	**CP-2020-11-24-54** **Date: 08-07-20**
Customer	:	Assistant Executive Engineer, Yelahanka Sub Division, BBMP, Bangalore.
Address	:	Yelahanka Sub Division, BBMP, Bangalore.
Project Name	:	"Improvements and Asphalting to Roads at Synika Vihara Badavane Main Road in Chowdeshwari Ward No -02 of Yelahanka Sub Division"
Agency	:	Sri. N. Thirunagendra, No:184, Besthara Beedhi, Yelahanka Old Town, Bangalore-560064
Customer's Reference	:	BBMP/EE/YNK.D/EPMT-01/W.O/87/2020-21
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	06-07-20
Sample Type	:	Fine Aggregate
Reference to BIS codes	:	IS 383 : 2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1, 3) RA2012 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption
Date of test	:	06-07-20
Total weight taken	:	1000 grams

Sl.no	Sieve Size	Weight Retained (gms)	Cumulative Weight Retained (gms)	% Cumulative Weight Retained	% Passing	Requirement as per IS 383:2016			
						Grading Zone I	Grading Zone II	Grading Zone III	Grading Zone IV
1	10 mm	0	0	0.0	100.0	100	100	100	100
2	4.75 mm	86	86	8.6	91.4	90-100	90-100	90-100	95-100
3	2.36 mm	145	231	23.1	76.9	60-95	75-100	85-100	95-100
4	1.18 mm	156	387	38.7	61.3	30-70	55-90	75-100	90-100
5	600 micron	188	575	57.5	42.5	15-34	35-59	60-79	80-100
6	300 micron	175	750	75.0	25.0	5-20	8-30	12-40	15-50
7	150 micron	162	912	91.2	8.8	0-10	0-10	0-10	0-15
8	Pan	88	1000	100.0	0.0	---	---	---	---

Result :The tested Sample Conforms to Grading Zone II

AE-2

AE-02

CIVIL Pro Sig. Date BANGALORE